

# NIGHTINGALE SUPPLY

PO BOX 712 HAMILTON CENTRAL 4007

PHONE: 3260.6544 FAX: 3260.6646

## Latex 60 Adhesive

- **DESCRIPTION:**

**LATEX 60 ADHESIVE** is used for adhering underfelt for most surfaces. It may also be used to prevent fraying of the edges of woven carpets and for patching and repairing fabrics such as canvas.

- **SPECIFICATION:**

APPEARANCE:	Milky White (ammonia odour)
BASE:	Natural latex
VISCOSITY:	60 - 120 cps
SPECIFIC GRAVITY:	0.93 - 0.96
SOLIDS:	61% ± 1%
DRYING TIME:	20 – 40 minutes
CLEAN UP:	Clean tools and equipment immediately with cold water
SHELF LIFE:	12 months in un opened drum at 20°C
PACK SIZES:	210LT Drum, 20 LT, 4 LT, 1 LT.

- **DIRECTIONS FOR USE:**

All subfloor surfaces must be clean, dry, smooth and sound; free from dirt, wax, grease, oil and any loose material. The subfloor must also be free from hydrostatic pressure or capillary action. The adhesive should not be used in excessive cold or hot conditions ie below 8°C or above 28°C.

It is recommended that highly porous timber or concrete subfloor surfaces be primed with Primer 88 and allowed to cure before applying adhesive.

Uneven or damaged floors should be repaired with a cementitious leveling compound. All subfloors should be tested for moisture content prior to surface priming or application of adhesive. All subfloors should be in accordance with current Australian standard installation practices (AS/NZS 2455.1:1995).

- **APPLICATION:**

Shake well before using. Apply a liberal layer on subfloor surface. Spread with a sponge or roller and press underfelt while still wet. Adhesion occurs immediately but full strength is not attained for several hours.

- **PRECAUTIONS:**

In common with all rubber based products contamination with extremely low concentrations of copper, manganese, brass and zinc will cause rapid ageing of the rubber.

- **CAUTION:**

DO NOT allow adhesive to freeze, unaffected by freezing when dry.

The information presented is believed to be accurate, however, no guarantee is implied or given. User should conduct their own testing to determine the suitability of any product for a particular purpose.